

**Profile** Profile® Blend with Tack **Hvdraulic Mulch** 



Solutions for your Environment"

Description

Profile<sup>®</sup> Blend with Tack is a biodegradable, Hydraulic Mulch (HM) composed of 100% recycled Thermally Refined<sup>™</sup> virgin wood fibers, cellulose fibers and wetting agents (including high-viscosity colloidal polysaccharides). The HM is made in the US, plastic-free, and phytosanitized to eliminate potential weed seeds and pathogens. Upon application, the product forms an intimate bond with the soil surface to create a porous, absorbent and flexible erosion resistant blanket that allows for rapid germination and accelerated plant arowth.

## Recommended Applications

- Erosion control and revegetation for mild slopes (≤3H:1V)
- Rough graded slopes •
- Enhancement of vegetation establishment

## **Technical Data Physical Properties\* Test Method** Units **Tested Value** ASTM D65661 g/m<sup>2</sup> (oz/yd<sup>2</sup>) Mass/Unit Area ≥ 280 (8.3) Water Holding Capacity **ASTM D7367** % ≥ 1,000 Material Color Observed n/a Green **Performance Properties\*** Units **Tested Value Test Method** Cover Factor<sup>2</sup> ≤ 0.35 ASTM D8298-Type 1 n/a Percent Effectiveness<sup>3</sup> ASTM D8298-Type 1 ≥ 65 % % Vegetation Establishment **ASTM D7322** ≥ 200 Functional Longevity<sup>4</sup> **ASTM D5338** ≤ 3 months **Tested Value Environmental Properties\* Test Method** Units Ecotoxicity<sup>5</sup> EPA 2021.0 n/a Non-Toxic ASTM D5338 Biodegradability Yes n/a CERTIFIED USDA BioPreferred® BIOBASED % **ASTM D6866** 98 PRODUCT **Biobased Content Elemental Impurity Limits ASTM D8082** Pass/Fail Pass **Product Composition Typical Value** Thermally Processed Wood Fibers (within a pressurized vessel) <sup>6</sup> 67% (minimum) Cellulose Fiber (maximum) 30% Wetting Agent- Including high-viscosity colloidal polysaccharides 3% \* When uniformly applied at a rate of 2,500 pounds per acre (2,800 kilograms/hectare) under laboratory conditions. 1. ASTM test methods developed for Rolled Erosion Control Products that have been modified to accommodate Hydraulic Erosion Control Products. 2.Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface. 3. % Effectiveness – One minus Cover Factor multipleid by 100%. 4. Functional Longevity is the estimated time period, based upon field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as sile-specific conditions, including; but not limited to – temper-ature, mosture, light conditions, soils, biological activity, vegetative establishment and other environmental factors. 5. 48-bout Co.g. 100% - LC.g. Profiles to the percent concentration of a substance in water when 50% percent mortality of an organism is reached, 50% mortality of the tested species (Dephnia magne) could not be achieved when subjected to 100% different development and organism is reached, 50% mortality of the tested species (Dephnia magne) could not be achieved when subjected to 100% different development and and the reactive approximation of a substance in water when 50% percent mortality of an organism is reached, 50% mortality of the tested species (Dephnia magne) could not be achieved when subjected to 100% different development and and the reactive approximation of the substance in water when 50% percent mortality of an organism is reached, 50% mortality of the tested species (Dephnia magne) could not be achieved when subjected to 100% different development and the percent concentration of a substance in water when 50% percent mortality of an organism is reached, 50% mortality of the tested species (Dephnia Magne) could not be achieved when subjected to 100% different development and the substance in the subjected to 100% different development and the subjected to 100% different dev Made in USA effluent concentration proving the material to be acutely non-toxic. 6. Heated to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa) in order to be Thermally Refined™/Processed and to achieve phytosanitation. **Packaging Data**

Properties	Test Method	Units	Nominal Value
Bag Weight	Scale	kg (lb)	22.7 (50)
Bags per Pallet	Observed	#	40
UV and weather-resistant plastic bags. Pallets are weather-proof stretch wrapped with UV resistant pallet cover.			

## **Profile Products**

750 Lake Cook Road, Ste. 440 Buffalo Grove, IL 60089 800-508-8681 or +1-847-215-3464 www.profileproducts.com

USDA

## To the best of our knowledge, the information contained herein is accurate. However, Profile Products cannot assume any liability whatsoever for the accuracy or completeness thereof. Final determination of the suitability of any information or material for the use contemplated, of its manner of use and whether the suggested use infringes any patents is the sole responsibility of the user. Profile Products 2021©